



TECHNICAL DATASHEET

EURO 844 LIQUID PUTTY

ART. NO: #138.844 (1KG)

EURO 844 LIQUID PUTTY is a two component polyester finishing putty designed specifically for the professional. With excellent adhesion to metal, body filler, wood, fiberglass, catalyzed primers and old/sanded OEM topcoats, EURO 844 provides an ultra-smooth finish that is easy to sand while simultaneously preventing sandpaper clogging. BPO pink hardener included.

FEATURES

- ✓ Ultra-smooth finish
- ✓ Easy sanding without abrasive paper clogging
- ✓ Minimizes the adhesion of contaminants to the base/clear coat
- ✓ Less primer is required
- ✓ Saves on sanding time
- ✓ Reduces the need for refinishing
- ✓ Improves the effectiveness of the primer

AREA OF APPLICATION

Liquid putty is designed for filling small surface imperfections like scratches, pinholes, sanding marks and shallow dents before applying primer as well as to improve the primer coat. It can be used to fill imperfections that are approximately 3mm deep.

CONDITIONS OF USE AND CONFORMITY

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgment in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

HEALTH & SAFETY

See Safety Data Sheet and labels for additional safety information and handling instructions. Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry. Wear appropriate PPE such as eye and skin protection. In the event of injury, see first aid procedures on SDS. Always observe all applicable precautions and follow good safety and hygiene practices.

| VOC INFORMATION | | |
|-----------------|-------------------|---------|
| Category | Putties & Fillers | |
| | g/L | LBS/GAL |
| VOC | 30.0 | 0.25 |
| Density | 1100 | 9.17 |

PRODUCT DATA

Nature: Thixotropic Liquid

Color: Light Beige

Shelf Life: Minimum 12 months (sealed in original container) between 5 - 30°C

Package: 1KG + BPO Pink Hardener

Number per case: 8

Safety Data Sheet (SDS) is available on our website

CAUTION

DO NOT POUR REMAINS OF THE READY MIXED MATERIAL BACK INTO THE BOTTLE. KEEP THE CONTAINER CLOSED AND STORE IN A COOL, DRY PLACE.

HANDLING



PREPARATION

1. Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent.
2. Thoroughly dry the surface before repairing. Keep the repair area small.
3. Sand all traces of rust, old putty, nitrocellulose paint, 1K acrylic synthetic paint and any layers reactive to cleaning solvent.
4. Keep the repair area small. Sand the entire repair area with P40. Use P80 to remove coarse sanding marks and bevel the coat inward toward the repair.


N.B. Since all polyester resin-based materials are sensitive to moisture, it is preferable to clean the steel by sandblast before applying the filler in order to avoid the formation of blisters or pinholes.



MIXING

1. Shake the putty and knead the cream hardener before using.
2. Add 2 to 3% by weight of BPO pink cream hardener (add a ribbon of cream hardener from edge to edge across the center of a 4" diameter puddle of putty).
3. Mix thoroughly until uniform color is achieved.

N.B. An overdose of cream hardener should be avoided. This may result in bleeding through and color changes in the top coat. Insufficient addition of hardener may result to a sticky resin layer on the surface.



WORKING TIME

4 - 5 minutes @ > 21°C (>70°F)

REACTION TEMPERATURE

At least >10°C (>50°F) and up to 90% relative humidity.

N.B. In winter it is preferable to warm the metal surface using infrared lamps (or other heat lamps) before application.



APPLICATION

Apply thin layers of the putty and spread evenly and smoothly. Do not blob on or apply all at once.



DRYING TIMES

15 - 25 minutes at > 21°C (>70°F) room temperature.

N.B. The heat will shorten the cure time while the cold will lengthen it.



SANDING

Before sanding, the product should cure at least 20 - 30 minutes at an ambient temperature of 21°C (70°F) or more.

First Sanding: P120 - P180

Final Sanding: P180 - P240